

Detailed Surface Composition Table

Description: Native Aluminium Oxide / Aluminium (Al) Foil (kitchen type foil)  
35 deg TOA  
Date: Fri Jan 29 1993

<u>Signal</u>	<u>Corrected</u> <u>BE</u>	<u>Exper.</u> <u>BE</u>	<u>Sens</u> <u>Factor</u>	<u>Norm</u> <u>Area</u>	<u>Relative</u> <u>Area</u>	<u>Atom</u> %
O Auger	980.9	980.9	0.00	23810	0	
O loss	554.3	554.3	0.00	34992	0	
* O 1s	532.6	532.6	2.12	105305	49672	44.02
* C 1s	285.9	285.9	1.00	30956	31002	27.48
* Al2s	119.9	119.9	0.90	28981	32155	28.50
Al2p	75.0	75.0	0.67	16955	25211	
O 2s	24.1	24.1	0.18	5178	28105	
O 2p	7.8	7.8	0.03	1748	68842	







